

DARLEY REFRACTORIES AUSTRALIA PTY. LTD.

A.C.N. 104 582 023 A.B.N. 85 104 582 023



P.O. Box 291
58 Grey Street
Bacchus Marsh Vic. 3340

Telephone: (03) 5367 2300

Facsimile: (03) 5367 2991

Email: darley@darleyrefractories.com.au

Web: www.darleyrefractories.com.au

PRODUCT:

AIRSET

CLASSIFICATION:

Pre-mixed air-setting medium duty refractory mortar.

INSTALLATION REQUIREMENTS:

Mortar Required per 1000 RMA 135 Brick

Trowelled Joints 250 kg

Dipped Joints 170 kg

Water addition for Dipped Joints
2.5 Litres/20kg pail

PROPERTIES:

Modulus of Rupture

Dried 2.5 Mpa

Fired 1400⁰C 7.0

SCREEN ANALYSIS:

95% minus 1mm

CHEMICAL COMPOSITION:

(Typical)

Silica 72%

Alumina 22

Accessory Oxides 6

Note:

The above data is typical for this product and is not a guaranteed specification and is subject to reasonable variation.