

# DARLEY REFRACTORIES AUSTRALIA PTY. LTD.

A.C.N. 104 582 023 A.B.N. 85 104 582 023



P.O. Box 291  
58 Grey Street  
Bacchus Marsh Vic. 3340

Telephone: (03) 5367 2300

Facsimile: (03) 5367 2991

Email: [darley@darleyrefractories.com.au](mailto:darley@darleyrefractories.com.au)

Web: [www.darleyrefractories.com.au](http://www.darleyrefractories.com.au)

## PRODUCT

## DARLEY 26

## CLASSIFICATION

Dry Press Medium Duty Fireclay Refractory

## TYPICAL TECHNICAL DATA:

### CHEMICAL COMPOSITION

	%
Silica	73
Alumina	23
Ferric Oxide	1.5
Titania	1.1
Accessory Oxides	1.2

### PHYSICAL PROPERTIES

Bulk Density	1,860	kg/m <sup>3</sup>
Apparent Porosity	28	%
Cold Compressive Strength	15	Mpa
Modulus of Rupture	5	Mpa
P.C.E.	29	Orton (1660°C)
Permanent Linear Change On Reheating to 1400°C/5hr	-0.3	%
Thermal Conductivity (*) @750°C Mean Temperature	1.03	W/m.°K

The above data is derived from routine testing of standard brick and is not a guaranteed specification. Unless agreed otherwise, supply and testing will be to the appropriate Australian Standard.