

DARLEY REFRACTORIES AUSTRALIA PTY. LTD.

A.C.N. 104 582 023 A.B.N. 85 104 582 023



P.O. Box 291
58 Grey Street
Bacchus Marsh Vic. 3340

Telephone: (03) 5367 2300
Facsimile: (03) 5367 2991
Email: darley@darleyrefractories.com.au
Web: www.darleyrefractories.com.au

PRODUCT

DENSECRETE 135

DESCRIPTION

A high temperature, high strength refractory castable comprised of hydraulic setting high alumina cements and dense, hard refractory aggregate.

MAXIMUM RECOMMENDED SERVICE TEMPERATURE*

1350⁰C

TYPICAL PROPERTIES:

Bulk Density (cast & dried @ 110 ⁰ C)	2,010	kg/m ³		
	<u>110</u>	<u>1050</u>	<u>1350</u>	⁰ C
Cold Compressive Strength	35	15	35	MPa
Modulus of Rupture	5	3	7	MPa
Permanent Linear Change After heating for 5hr @	Neg.	-0.2	±1.0	%

THERMAL CONDUCTIVITY: (On cooling from 1050⁰C)

@ Mean Temp	400 ⁰ C	900 ⁰ C
	0.91	0.97W/m. ⁰ K

TYPICAL COMPOSITION:

Alumina	40	%
Silica	43	
Calcia	9	
Ferric Oxide	6	

NOTE: Data is derived from routine testing of regular grade mixes and is not a guaranteed specification.

WATER ADDITION (Ball-in-hand consistency) 15-16%