

DARLEY REFRACTORIES AUSTRALIA PTY. LTD.

A.C.N. 104 582 023 A.B.N. 85 104 582 023



P.O. Box 291
58 Grey Street
Bacchus Marsh Vic. 3340

Telephone: (03) 5367 2300
Facsimile: (03) 5367 2991
Email: darley@darleyrefractories.com.au
Web: www.darleyrefractories.com.au

TYPICAL FIRECLAY ANALYSIS FOR HALLAM & ROWSLEY CLAY CONSISTENT OVER THE LAST 20 YEARS.

	<u>HALLAM CLAY %</u>	<u>(ROWSLEY) CLAY %</u>
Loss On Ignition	8.1 - 0	6.6 - 0
Silica	66.5 - 72.4	65.7 - 70.3
Alumina	21.6 - 23.5	22.0 - 23.6
Ferric Oxide	1.72 - 1.87	0.95 - 1.02
Titania	0.87 - 0.95	1.18 - 1.26
Calcia	0.03 - 0.03	0.12 - 0.13
Magnesia	0.15 - 0.16	0.48 - 0.51
Soda	0.08 - 0.09	0.25 - 0.27
Potash	0.37 - 0.40	2.24 - 2.40
Other	0.01 - 0.01	0.01 - 0.01